

# GOIN International Vietnam Co., Ltd. Tel.:

R204, NC Building, No. 80, Ha Dac St., District 12, HCM City

Tax-Code: 0314463947

E-mail: tony.nguyen@goin-mail.com


(+84) 862575751

Web: www.goin-vn.com

# KES-F7

### Thermo Labo

The sensation of coldness or warmth when skin is touching an object, is referred to as the "coldness and warmth feeling", which varies depending on the amount of heat transferred from the skin to the object. This device measures such feeling by evaluating the "q max" value (peak heat flux).



# **FEATURES**

# A design that mimics the human sense of actually touching an object

The load and contact area of the KES-F7's heat plate, which is brought into contact with the target sample, is designed to imitate the sensation of touching an object by hand, allowing for more realistic measurements of maximum heat transfer amounts.




Thermal With constant thermal conductivity measurement, the ease at which heat is transmitted from a heat plate with a constant temperature conductivity: (30°C) through a sample to another heat plate with a separate constant temperature (20°C).

Heat retention properties:

(optional accessory)

The sample is set on a heat plate with a constant temperature (room temperature plus another 10°C) and is left in contact with the air. A constant wind is then applied continuously to the sample surface. The amount of heat lost through the sample is then measured in order to calculate the heat retention rate (%). Measuring methods include a dry method that assumes direct contact is made between dry skin and clothing and a wet method that assumes contact is made between sweaty skin and clothing.

### SYSTEM CONFIGURATION DIAGRAM / MEASUREMENT DATA



# KES-F7 Thermo Labo

Dimensions/	Wei	igh
(approx.)		

- · Thermo Labo (qmax / thermal conductivity measurement unit): W230 × D360 × H80 (mm) / 3 kg \*With BT-box and T-box set on base plate Amplifier: W180 × D400 × H400 (mm) / 15 kg
- · Heat Retention Property Measuring Unit\*: Wind Tunnel Unit: W460 × D320 × H1100 (mm) / 7 kg Wind Tunnel Amplifier: W125 × D200 × H100 (mm) / 1.3 kg
- Thermo Cool: W180 × D180 × H110 (mm) / 2.5 kg Thermo Cool Amplifier: W230 × D310 × H220 (mm) / 5 kg

#### Power source

100 VAC

(Thermo Labo unit) Max. power consumption: 50W (Wind tunnel unit) Max. power consumption: 20W\* (Thermo Cool unit) Max. power consumption: 20W

#### Measurement environment temperature and humidity

20 to 30°C / 50 to 70  $\%\,$  RH. (No condensation.) Temperature and humidity should be kept constant during measurement.

(Standard temperature and humidity conditions: 20°C / 65% RH) \*The instrument should be located to minimize influence from wind or vibrations.

<sup>\*</sup>Optional accessory: Heat Retention Property Measuring Unit (Wind Tunnel Unit, Wind Tunnel Amplifier)

Measurement unit	T-Box: (T-plate 3 × 3 cm)
configuration	5 cm BT-Box: (BT plate 5 × 5 cm)
	10 cm BT-Box: (BT plate 10 $\times$ 10 cm)*
Temperature display	Unit: Degrees Celsius
	Min. display: 0.1°C
	Max. temperature set point: 40°C
Evaluated coldness/	q max [W/cm²]
warmth feeling value	
Heater control method	Output in voltage proportional to temperature difference
Heat-loss display	Max. usable range (200mW range): Approx. 200mW
	Max. usable range (2W range): Approx. 2W
	Max. usable range (20W range): Approx. 10W
	*Do not use the 200W range.
Measurement range	Thermo Labo unit: Max. 10 W
	(stable measurable range: 3 W (1.2 kW/m²) or less)
	Wind tunnel speed: Max. 1 m/sec*
	Thermo Cool: Min. temperature setting (5°C) to room temperature
	Dimensions: 180 × 180 mm, Thickness: 2 mm (max.)



For safety use, please read the operation manual / the instruction carefully and throughly before using the tester.

Specification details recorded here are subject to change without notice.





GOIN International Vietnam Co., Ltd.

R204, NC Building, No. 80, Ha Dac St., District 12, HCM City Tax-Code: 0314463947